

HONEY 8 DESIGNER COLORS

Thickness	Hide type	Average size
0.9 – 1.1 mm	European Bovine	4.6-5 sqmt (48-55 sqft)

Water and stain re	epellent already dyed into leather
RESIDENTIAL – CON	TRACT – HOSPITALITY – FASHION

TECHNICAL SPECIFICATIONS

Test	Test method	Measurement	Result
		unit	
Tear strenght-Single edge tear	UNI EN ISO 3377-1	N	> = 20
Colour fastness to rubbing dry 50	UNI EN ISO 11640:1998	Grey scale	> = 3/4
cycles			
Colour fastness to rubbing wet 20	UNI EN ISO 11640:1998	Grey scale	> = 3
cycles			
Colour fastness to rubbing sweat	UNI EN ISO 11640:1998	Grey scale	> = 3
20 cycles	ISO 11641 pH8		
Flexing endurance dry 50.000	UNI EN ISO 5402		No damage
cycles			
Colour fastness to artificial light	UNI EN ISO 105 B02 (MET5)	Blue scale	> = 2
Exposition energy 16.000 kj/sqm			
Burning behaviour to cigarette and	BS 5852:1979		Pass
match flame	BS EN 1021-1-2-:2006		

The test results are referred only to the sample tested

THE PRODUCT COMPLIES WITH THE REACH REGULATION

LEATHER
MADE IN ITALY

www. the shann group. com