

CASA 48 DESIGNER COLORS

Thickness	Hide type	Average size
0.9 – 1.1 mm	Asian Bovine	3.8 – 4.0 sqmt (40 – 43 sqft)

<i>Water and stain repellent already dyed into leather</i>
HIGH TRAFFIC AREA FRIENDLY
RESIDENTIAL – CONTRACT – HOSPITALITY –FASHION

TECHNICAL SPECIFICATIONS

Test	Test method	Mesurment unit	Resoult
Tear strenght-Single edge tear	UNI EN ISO 3377-1	N	➤ = 20
Colour fastness to rubbing dry 500 cycles	UNI EN ISO 11640:1998	Grey scale	➤ = 4
Colour fastness to rubbing wet 250 cycles	UNI EN ISO 11640:1998	Grey scale	➤ = 4
Colour fastness to rubbing sweat 80 cycles	UNI EN ISO 11640:1998 ISO 11641 pH8	Grey scale	➤ = 4
Flexing endurance dry 50.000 cycles	UNI EN ISO 5402		No damage
Finish adhesion dry	UNI EN ISO 11644	N/Cm	➤ = 2
Colour fastness to artificial light Exposition energy 16.000 kj/sqm	UNI EN ISO 105 B02 (MET5)	Blue scale	➤ = 5
Burning behaviour to cigarette and match flame	BS 5852:1979 BS EN 1021-1-2-:2006		Pass
	NFPA 260		Pass
	CAL TB 170		Pass
	FAR 25.853 (a) and FAR 25.853 (b) APPLICABLE ON REQUEST		

The test results are referred only to the sample tested

THE PRODUCT COMPLIES WITH THE **REACH** REGULATION

**LEATHER
MADE IN ITALY**