

 	<b>Data Sheet</b>	<b>Internal Spec</b>	<b>Date</b>	<b>Drafted</b>	<b>Verified</b>	<b>Approved</b>
	S4030I_a	Classe 10	02/09/13	RQ	LAB	UT
<b>NEW VICTORIA / SUAVE</b>						

**DESCRIPTION**

Grain leather chrome tanned

**TO BE USED FOR**

Furniture

Parameter	Method	Value	U.M.
Tear strength - single edge	UNI EN ISO 3377-1	≥ 20	N
Colour fastness to rubbing - dry @ 500 cycles	UNI EN ISO 11640:1998	≥ 4	g.s.
Colour fastness to rubbing - wet @150 cycles	UNI EN ISO 11640:1998	≥ 4	g.s.
Colour fastness to rubbing - perspiration @80 cycles	UNI EN ISO 11640:1998 - 11641 (pH8)	≥ 4	g.s.
<i>Flex resistance - dry @50000 cycles</i>	UNI EN ISO 5402	No damage	
Adhesion of finish - dry	UNI EN ISO 11644	≥ 2	N/cm
Colour fastness to artificial light Exposition energy 16.000 kJ/m <sup>2</sup>	UNI EN ISO 105B02 (MET. 5)	≥ 4/5	g.s.
Fire Safety - Burning behaviour cigarette and match flame (this norm refers exclusively to the combination leather and padding)	BS 5852:1979 Match & Cigarette test  BS EN 1021-1-2:2006 Match & Cigarette test	Pass	

*Abbreviations*

*ppm = part per million*

*g.s. = grey scale ISO 105-A02:1993*

*b.s. = blue scale ISO 105-B02:1994 §4.1.1*

*ND = Not Detectable*

THE VALUES REPORTED IN THIS DOCUMENT CAN CHANGE ACCORDING TO THE COLOUR, THE THICKNESS AND OTHER PARTICULAR REQUESTS OF THE CUSTOMER. IN CASE THIS DOCUMENT SHOULD REPRESENT A CONTRACTUAL REQUIREMENT IT MUST BE CLEARLY QUOTED IN CUSTOMER ORDER.